

PRODUCT DESCRIPTION

Coppriint LF-370 provides the following product characteristics:

Technology	Screen printing
Appearance	Copperish paste
Filler Type	Copper
Product Benefits	<ul style="list-style-type: none"> • Ultra high conductivity • Excellent adhesion • Excellent printability with screen printing
Drying	Ceramic lamps/hot air/thermal plate
Sintering	R2R or Heat press
Application	Conductive Ink
Key Substrates	FR4
Typical Assembly Applications	FPCB and PCB

Coppriint LF-370 screen printable paste is formulated to provide high electrical conductivity.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Average particle Size, μm	D50 < 0.15, D90 < 5.0
Solids Content, after 30 minutes @ 150°C, %	88±1
Density, g/ml	3.7
Viscosity @ 25°C, DVEHA Brookfield spindle 14, 100rpm, mPa·s (cps)	7000-10000
Theoretical coverage @ 8 μm dry film thickness,	12 m ² /kg
Shelf Life @ -10°C, days	180
Flash Point - See SDS	

RECOMMENDED CURING

Drying cycle
120sec @85°C (Hot air, Reflow oven)

Sintering cycle
5 sec @300°C (R2R laminator) or 5-30 sec @ 280-320°C (Heat press)

The above drying is a guideline recommendation. Conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer drying equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL Physical Properties

Adhesion, (tape test 3M Scotch 234)	pass
Cross cut test ISO 2409-2007	5b

Electrical Properties

Sheet Resistance, ohm/sq/25 μm	<0.0025
---	---------

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE

Preparation guidelines

1. Coppriint LF-370 is supplied as "Sinter ready" formulation ready for use.
2. Mix formulation prior print.
*Detailed procedure can be found in Application Notes

www.coppriint.com

Application (screen properties)

Emulsion, Solvent and Water resistant emulsion, μm	10 to 40
Squeegee Shore Hardness	70 to 90
Screen Type, Polyester screen, mesh	100 to 300

CLEAN-UP

The equipment can be cleaned with Dowanol DB followed by water.

STORAGE:

Store product in the tightly closed container in a dry location below -10°C. Open the container carefully. Storage information may be indicated on the product container labeling.

Optimal Storage: below -10°C. Storage above -10°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Coppriint cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated.

Not for product specifications

The technical data contained herein are intended as reference only

